# Tribological Behavior and Performance of Lubricants Filled with Nanoparticles: A Review

Nabhan A.<sup>\*</sup>, Ameer A. K., Badran A., Rashed A.

Production Engineering and Mechanical Design Department Faculty of Engineering, Minia University, El-Minia 61111, Egypt. \*Corresponding authors: Email: a.nabhan@minia.edu.eg

**ABSTRACT :** Analyzing the tribological characteristics of lubricants and trying to control their properties plays a vital role to reduce the dissipated heat generated from the wear and the friction between the rubbing surfaces of sliding parts and thus prevent engine power loss. This work aims to review the recent trend of studies that focus on nano-lubricants to improve the friction characteristics and wear resistance of rubbing parts. Several nanoparticles NPs, such as ZnO, SiO<sub>2</sub>, TiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, graphene, and CuO have been used as lubricants additives which resulted in an enhancement in the tribological properties (i.e. wear and friction) and thus work as a promising lubrications. Adding NPs to lubricants play an excellent role and improve the raibological performance in terms of increasing load carrying capacity under high operating temperatures. The nanoparticles have not only the ability of carrying loads but also separate the asperities surfaces to confirm the anti-wear and antifriction due to the nanoparticles rolling effect. Nanoparticles NPs additives in the engine oil reduce friction and wear in mixed and boundary lubrication regimes. Friction can be reduced by about 40%, and the wear could be reduced by over 50% via the addition of nanoparticles. **KEYWORDS** Nanoparticle additives, grease, engine oil, wear rate.

Date of Submission: 04-01-2021

Date of acceptance: 19-01-2021

#### I. INTRODUCTION

Continuous pursuit of developing and finding solutions to sudden failure of the bearings in the recent times, one of the most important areas of research studies. The general classes of bearings are journal bearing, rolling element bearing, fluid bearing, and magnetic bearing, [1]. Therefore, the bearings used in any equipment must have several factors such operating speeds, the ability to carrying loads, operating temperatures and various environment conditions. The condition monitoring of rolling element bearings and its faults was detected using vibration analysis, [2, 3]. A journal or friction bearings consists of a bushing, sleeve, supported by a housing, which make use of a pressure wedge of fluid that forms between the rotating shaft and the bearing. The general classes of journal bearings are divided into hydrodynamic bearings, hydrostatic bearings and hybrid bearings, [4]. Rubbing of two interacting surfaces that are loaded by a normal force, acting on the normal direction to the contact area, causes energy dissipated through friction and wear in the form of heat. Therefore, the interacting surfaces must be completely separated by the existence of a film of fluid, [5].

High-performance lubrication oils and grease are capable of inducing the required reactions on the mating surfaces, thus providing reliable damage protection even under severe operating conditions, [6, 7]. Due to the rolling effect of nanoparticles in the lubricated contact surfaces could prevent direct contact and reduce friction coefficient and wear rate. So, the addition of nanoparticles leads to more smooth sliding and prevent metal-to-metal contact, and tribological properties of lubrication system can be enhanced, [8].

#### **II.** LUBRICANT OILS

In automotive engines, the conventional lubrication properties are still not much satisfactory to reduce machine elements friction and wear resistance. Machine element possess a wide range of temperature and bearing load which owing to a lubrication with specific properties such as; good wear resistance, superior bearing load ability, environmentally friendly, and good compatible with the contact surfaces. Energy conservation has great attentions nowadays due to the energy dissipation in internal combustion engine is directly effect on engine performance. Based on the characteristic chemical compounds, the various types of

2021

nanomaterials have been classified into metals, metal oxides, carbon-based, ceramics and polymers, [9]. Nanolubricants by means of colloidal suspensions with a nanomaterial such as SiO<sub>2</sub>, TiO<sub>2</sub>, ZrO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub> and CuO NPs resulted in an improvement in the tribological properties (i.e. wear and friction) and thus work as a promising lubrications.

Nanoparticles NPs additives in the engine oil reduce friction and wear in mixed and boundary lubrication regimes. Friction can be reduced by about 30%, and the wear of the base oil could be reduced by over 50%, [10]. These improvements in the tribological properties of engine oils after dispersion of NPs is mainly attributed to the rolling effect of nanoparticles. The rolling of nanoparticles in the moving surfaces could form a thin-film on the rubbing surfaces which characteristic with a low friction coefficient, [11]. The tribological performance of lubricant oils filled by PTFE nanoparticles was enhanced, which leads to an increase in capacity of the high loads compared with the other nanoparticles, [12–15].

# 1. Al<sub>2</sub>O<sub>3</sub> NPs Additives to Engine Oils

The lubricant oil, SAE 20W40, with using  $Al_2O_3$  nanoparticles with 20 nm of grain size as nanoadditives were studied. The results showed that 0.5% wt. of  $Al_2O_3$  nano-lubricant reduce the friction by 49.1% and 21.6% under flooded and starved conditions, as compared to SAE 20W40 lubricant oil [16]. The wear rate was reduced by using 0.5% wt. of  $Al_2O_3$  nano-lubricant with 40–80 nm of grain size [17]. Adding of 0.1wt% concentration and 78 nm grain size of  $Al_2O_3$  nanoparticle to engine oil leads the friction coefficient to decrease by ranges of 17.61% and 23.92% for the four-ball and the thrust-ring test, respectively [18]. The thermal conductivity improved by 37.49% using 3.0% wt. of  $Al_2O_3$  nano-lubricant [19]. Nanoparticles can easily enter into small gaps between sliding surfaces because of their ultrafine sizes, whereas the micron-scale traditional additives cannot [20].

A study of influence of mixed temperatures on the tribological performance of  $Al_2O_3$  nano-lubricants under different operating conditions by using friction and wear tribometer. It was found that  $Al_2O_3$  added to 20W-50 engine oil enhanced frictional property significantly and reduced vibrations. The study concluded that the lowest coefficient of friction was obtained at 0.4 wt. % concentration of  $Al_2O_3$  nanoparticles and working temperature of 50°C [21]. The tribological performance of 20W-50 engine oil by the addition of  $Al_2O_3$ nanoparticles were studied. The experiments have been performed on the samples lubricated by different nanolubricants prepared by dispersing the nanoparticles at three different mixed temperatures of 50°C, 100°C, and 150°C. It was found that the lowest wear rate is achieved when the sliding surfaces were lubricated by the nanolubricants mixed at temperature of 50°C. It can be found that the wear rate reduces by 34.4% during the lubrication by nanolubricants containing 0.4 wt.% of  $Al_2O_3$  nanoparticles content, [22].

## 2. TiO<sub>2</sub> NPs Additives to Engine Oils

The nano-lubricant oil contents of TiO<sub>2</sub> nanoparticles reduce friction coefficient clearly, it may be due to form of a thin film on contact surfaces [23, 24]. The results of engine oil dispersing by TiO<sub>2</sub> nanoparticles showed the ability to withstand higher loads by of 35%, [25]. The effect of spherical titanium oxide nanoparticles, the average diameter was 50 nm, in reducing friction between two pieces of cast iron were evaluated. The rapeseed oil with 5wt% of TiO<sub>2</sub> nanoparticles concentration reduces the mean surface roughness by 80.84%, [26]. While, the friction coefficient and the wear scars decreased approximately by 15.2% and 11%, respectively [27]. TiO<sub>2</sub> nanoparticles can improve the tribological performance of lubricating oil, Shell Helix HX3 20W-50 and HX5 15W-50, via the reducing of friction coefficient and the wear rate. The 1.0 wt. % of TiO<sub>2</sub> nano-lubricant shows that the friction coefficient and wear rate decreased in the ranges 39 – 47% and 50 %, respectively, as compared to the additives free oil, [28].

# 3. SiO<sub>2</sub> NPs Additives to Engine Oils

The effect of dispersing diamond and  $SiO_2$  nanoparticles to paraffin oil on the tribological performance was investigated, [29]. It was found that paraffin oil using both nanoparticles as additives have friction coefficient and wear less compared with the pure paraffin oil. The nano-lubricant paraffin with  $SiO_2$ nanoparticles of 0.05 to 0.5 wt. % contents have the best tribological performance, [30]. The results can show that paraffin oil dispersing by tiny size of  $SiO_2$  nanoparticles anti-wear and anti-friction characteristics under high loads.  $MoS_2$  and  $SiO_2$  nano-lubricants used to study the frictional properties of contacts between magnesium alloy and steel using a reciprocating sliding ball-on-flat tribometer. The results showed that  $MoS_2$  nano-lubricants has more clearly effect as compared with the  $SiO_2$  nano-lubricants in terms of the load carrying capacity and the lubrication film stability, [31].

The rheological stability and friction coefficient of SAE 40 Lubricating oil using SiO<sub>2</sub> nanoparticles as additives with contents up to 1% by weight were studied, [32]. The fully flooded condition testing results can show that the friction coefficient decreased with the increase of the concentration of nano-lubricant up to 0.6% while the coefficient of friction starts increasing with nano-lubricant with content above 0.6%. The tribological

2021

properties, lubricating oil Shell Helix HX3 20W-50 and HX5 15W-50 filler with SiO<sub>2</sub> nanoparticles, improved as the lubricant composition of 0.5 wt. % SiO<sub>2</sub> nanoparticles while with increasing the composition of nanoparticles to 1.0 wt. % the friction coefficient and wear rate again increased., [28].

# 4. Some Other NPs Additives to Engine Oils

The PTFE nanoparticles are used as lubricant additive to enhance the tribological performance of oils, generally more effective in the extreme pressure then the other nanoparticles [33–36]. Copper oxide (CuO) used as nano-additives engine oil. Further it was found that CuO nanoparticles play a vital role for improving the tribological performance. The results display that nano-lubricant exhibits clearly reducing of coefficient of friction and anti-wear behavior by 53% and 24%, respectively [37–39]. Carbon-based, such as carbon nanotubes, carbon nanofibers, and graphene are distinguished to have an effective role in improving the thermal conductivity of the fluids [40]. In contrast, increasing amount of the carbon leads to reduce stability and do not useful in the viscosity of nano-lubricants [41, 42].

## 5. Hybrid NPs Additives to Engine Oils

In an attempt to reach the better results, it was using hybrid nano-additives that may combine carbon and other types of nanoparticles. Hybrid carbon nanotubes with TiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, and other nanoparticles play a desirable role in improve the pressure characteristics and increase its thermal conductivity [43–46]. Hybrid TiO<sub>2</sub>/SiO<sub>2</sub> nano-lubricants is considered a desirable way on the control the friction coefficient and wear resistance of rubbing surfaces [47]. The tribological properties of the modified Al<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> composite nanoparticles as lubricating oil additives were investigated by four-ball and thrust-ring tests in terms of wear scar diameter, friction coefficient, and the morphology of thrust-ring, [48]. Titanium and aluminum oxides nanoparticles are considered the most used as additives for motor oils due to their excellent tribological, chemical and thermal properties, [49]. The influence of using the hybrid of Al<sub>2</sub>O<sub>3</sub>/TiO<sub>2</sub> as a nano-additives in engine oil was investigated, [50, 51]. The results illustrated that the friction coefficient and wear rate of the ring decreased in the ranges 39–53% and 25–33%, respectively.

# **III.** LUBRICATING GREASES

The tribological behavior and lubrication mechanisms of main classes of nanoparticles as lubricating oil additive to reduce wear and friction. Addition of nano particles size, less than 100-micron size, have a great influence on viscosity, friction factor, wear and thermal properties like heat transfer of the lubricant. Nano particles helps in improving the life of the lubricating oil and consequently life of the bearing in machineries can save millions of dollars in emergency maintenance costs. The different methods for preparation of Nano-grease were investigated. The most commonly used method is the 'Direct mixing method'. In this method, the nano-particles are directly mixed with grease under heavy mechanical stirring, [52].

Influence of contaminants in the grease of the rolling bearing was investigated using the acoustic emission, [53]. It was found that, small size contaminant particles generated a higher acoustic emission pulse count level than large size particles. The behavior of lubricant contamination by solid Particles on the vibration signals of roller bearings was investigated, [54-55]. The experimental tests were performed with applied radial Load was 10% of the bearing nominal load. The roller bearings NU205 was used, which lubricated with mineral oil of different viscosity grades, [56-57]. Quartz powder in three concentration levels and different particle sizes was used to contaminate the oil, [58-59]. The dolomite powder in three concentration levels and different particle sizes was used to contaminate the grease with deep groove ball bearings, [60].

Different materials such as Silica, metal-burr, dolomite-powder, iron-ore, and sawdust, all at three concentration levels and different particle sizes were used to contaminate the lubricant, [61-62]. Polymeric materials such as polyethylene (PE), polytetrafluoroethylene (PTFE), and polymethylmethacrylate (PMMA) are the normally applied as enhanced additives. The PTFE thickener to form a chemically inert product was described, [63]. It was found that, the effect of the abrasive contaminants can be lowered by diffusing polymeric powders in the grease. However, the adding of polymer to lubricating grease at relatively high concentration (more than 35 wt. %) has no effect on the anti-wear action of the lithium grease. Besides, the adding of polymeric powder of particle size relatively greater than that of the contaminant can be considered as a useful method of eliminating the cutting process of sand particles.

## Various NPs Additives to Lubricating Greases

Advanced methods technologies used in today's high-performance grease are capable of inducing the required reactions on the surfaces of bearings, thus providing reliable damage protection even under severe operating conditions, [64–66]. The tribological behavior and lubrication mechanisms of main classes of lubricating grease based on nanomaterials to act on the surface of the friction pair due to its anti-vibration damping effect, which is different from the traditional load additives.

2021

 $Al_2O_3$  nanoparticles were used as filler contents in lithium grease. It is showed that the friction coefficient was decreased comparison with the base grease, [67]. Friction and wear tribometer tester, MRH-3, was used to study the tribological performance of lithium grease filled by various types of nanoparticles as additives. The addition of  $Al_2O_3$  nanoparticles showed that the improvement the antifriction behavior of the pure grease surface reconditioning ability, [68].  $Al_2O_3$  nanoparticles can enhance the lubricating ability of grease and reduce the degree of wear on the surface of the friction pair greatly, [69]. The tribological and rheological properties of nanorods– $Al_2O_3$  as a filler material in lithium grease at various contents were investigated. The grease sample with a 0.3 wt.% content of nanorods– $Al_2O_3$  exhibited the lowest average friction coefficient and wear scar diameter. The topography images indicate that the worn surface is more smooth and furrows and grooves are reduced. By increasing the temperature gradually, a chemical protective film was produced leading to the reduction in the friction coefficient of grease, [70].

The tribological properties of  $CaF_2$  nano-crystals as lithium grease additives on a four ball tester. Reduction of 29 % and 19 % in wear scar diameter and friction respectively was reported. The improvement in tribological properties of  $CaF_2$  added grease is not proportional to concentration of  $CaF_2$ . In general, there exists a limiting value of nano-additives up to which tribological properties can be improved, [71]. The tribological properties of the  $CaCO_3$  nanoparticles as an additive in lithium grease were evaluated with a four-ball tester, [72]. The results show that these  $CaCO_3$  nanoparticles exhibit good performance in anti-wear and frictionreduction, load-carrying capacity, and extreme pressure properties. The tribological properties of carbon nano tubes CNTs as an additive on lithium grease were evaluated with a four ball tester, [73]. The results show that the grease with CNTs exhibit good performance in anti-wear and decrease the wear scare diameter about 63%, decrease friction reduction about 81.5%, and increase the extreme pressure properties and load carrying capacity about 52% with only 1% wt. of CNTs added to lithium grease. Furthermore, the. The vibration amplitude was improved due to increase of concentration of carbon nanotubes CNTs, [74].

The tribological behavior of  $ZrO_2$  and  $TiO_2$  nanoparticle added to lithium grease was studied, [75]. Amorphous over-based calcium sulfonate (AOBCS) and crystalline over-based calcium sulfonate (COBCS), transformed from the AOBCS were used as filler materials in to lithium complex grease, [76]. The samples Li grease filled by COBCS showed a good role in reducing the friction and wear and good load-carrying capacity comparing to simple lithium grease. Moreover, the samples Li grease filled by AOBCS particles enhanced the tribological properties of more than the COBCS ones at same contents amount under applied load in contact area. The rheology of the lithium grease with addition of carbon nanotubes are affected by use of nano-additives [77]. As a result, its shear stress and apparent viscosity were increased up to 67% and 82%, respectively. Nano titanium, silicon and hybrid nano-oxides at five concentration levels were used to disperse the grease, [78].

Further, in the case of nanoparticles that has spherical shape, micro ball-bearing rolling effect, which helps contact surfaces behavior may also contribute to reduce the frictional properties of nano-grease [79,80]. Pure lithium grease was not able to provide effective lubrication above the high loads. However, lithium grease filled with nano-calcium borate exhibited better tribological performance compared with the base grease, [81]. According to the XPS analysis of contact surfaces, it can be notice that the boundary lubrication film is composed of deposited nano-calcium borate and reaction products such as  $B_2O_3$ , CaO and iron oxide. The multilayer graphene was used as nano-additives to lithium grease and bentone grease, [82]. Graphene shows good ability to form conformal protective layer on rubbing surfaces and secured enhancement in load carrying ability [82-83]. Further, use of TiO<sub>2</sub> and SiO<sub>2</sub> nanoparticles as filler contents, were not able to improve the load carrying capacity of titanium complex grease [84]. Thus, the ability to improve load carrying capacity by addition of nanoparticles depends upon the correct combination with the type of grease.

Depending on the combination of nanoparticles and grease, thermal conductivity of nano-grease may increase or decrease. CuO,  $Al_2O_3$ ,  $TiO_2$  and Multiwall carbon nanotubes (MWCNTs) as nano-additives to mobilgrease-28 showed an improvement in thermal conductivity of nano-grease; on the other hand, thermal conductivity was found to decrease for nano-grease based on Uniflor-8623B grease. Better thermal transport capacity of carbon nanotube added silicon thermal grease as compared to base silicon grease [85,86]. Adding nano-particles of Ag,  $Al_2O_3$ , CuO and MWCNTs to thermal grease (YG-6111) were reported enhancement in thermal conductivity. Among all the other tested nano-additives, MWCNTs was found to be the best additive to enhance the heat transfer capacity of base grease [87].

# **IV. CONCLUSION**

In the current study, the results obtained from recent developments in lubrication studies show that the tribological properties of lubricating engine oils and greases in case of nanoparticles were added to lubricating engine oils and greases. The reducing wear scar width at nano-samples affirms that the dispersion of nanoparticles in lubricating engine oils and greases can mostly minimize the friction performance, which exceedingly matches to the rolling effect ability of nanoparticles between the contact surfaces helps in delaying the damage of friction and wear. Considering nanoparticles is anti-wear additives can be explained by the

reformed of thin-films on the worn surfaces to prevent metal-to-metal contact between frictional surfaces. Furthermore, the addition of nanoparticles to lubricating engine oils and greases can fill scars and grooves of the worn surfaces on the contact area.

## REFERENCES

- Avraham Harnoy, Bearing Design in Machinery: Engineering Tribology and Lubrication, Marcel Dekker, Inc., 270 Madison Avenue, New York, NY 10016, 2003.
- [2]. Nabhan A., Nouby M., Samy A. M., and Mousa, M.O.," Vibration analysis of deep groove ball bearing with outer race defect using ABAQUS "Journal of Low Frequency Noise, Vibration and Active Control, 35(4). pp. 312-325, 2016.
- [3]. Nabhan A., Nouby M., Samy A. M., and Mousa, M.O.," Multiple Defects Detection in Outer Race of Gearbox Ball Bearing Using Time Domain Statistical Parameters" International Journal of Vehicle Structures & Systems, 8(3). pp. 167-174, 2016.
- [4]. Someya, Tsuneo Ed., Journal-Bearing Databook, Springer, 1989.
- [5]. Szeri, A.Z. Hydrodynamic and Elastohydrodynamic Lubrication. In Modern Tribology Handbook; Bhushan, B., Ed.; CRC Press: New York, NY, USA, pp. 383–453, 2001.
- [6]. Astakhov, M. V., 'Ultrafine powders and properties of lubricating oil', Avtomob. Promst. 2, pp. 4 23, 1994.
- [7]. Stachowiak G.W., Batchelor, A.W., Engineering Tribology, 4<sup>th</sup> edition; Elsevier, 2014.
- [8]. Guo, D., Xie, G., Luo, J., Mechanical properties of nanoparticles: basics and applications. J. Phys. D Appl. Phys. 47, 13001, 2014.
- [9]. Dai W., Kheireddin B., Gao H., Liang H., "Roles of nanoparticles in oil lubrication", Tribology international, 102, pp. 88–98, 2016.
  [10]. Liu TC, Wang JH, Shei JT, Wu YY. Friction and Wear Properties Study of Nanoparticles as Additive in Lubrication Oil. SAE
- Technical Paper 2006-32-0016, 2006. [11]. W. Khalid Shafi, M.S. Charoo, "Nano-Lubrication Systems: An Overview", Materials Today: Proceedings, 5, 20621-20630, 2018.
- [12]. Dubey M. K., Bijwe J., Ramakumar S. S. V., "PTFE based nano-lubricants", Wear, 306, pp.80–88, 2013. DOI: 10.1016/j.wear.2013.06.020.
- [13]. Dubey M. K., Bijwe J., Ramakumar S. S. V., "Nano-PTFE: new entrant as a very promising EP additive", Tribology International, 87, pp. 121–131, 2015. DOI: 10.1016/j.triboint.2015.01.026.
- [14]. Dubey M. K., Bijwe J., Ramakumar S. S. V., "Effect of dispersant on nano-PTFE based lubricants on tribo-performance in fretting wear mode", RSC Adv., 6, pp. 22604–22614, 2016. DOI: 10.1039/C5RA16795G.
- [15]. Saini V., Bijwe J., Seth S., Ramakumar S. S. V., "Role of base oils in developing extreme pressure lubricants by exploring nano-PTFE particles", Tribology International, 143, 106071, (2019). DOI: 10.1016/j.triboint.2019.106071.
- [16]. Mohan N., Sharma M., Singh R., Kumar N., "Tribological properties of automotive lubricant SAE 20W40 containing nano-Al<sub>2</sub>O<sub>3</sub> particles", SAE Technical Paper 2014-01-2781, 2014. DOI: 10.4271/2014-01-2781.
- [17]. Elwain S.E. M., Blanchet T. A., Schadler L. S., Sawyer W. G., "Effect of particle size on the wear resistance of alumina-filled PTFE micro and nano-composites", Tribology Trans, 51, pp. 247–253, 2008.
- [18]. Luo T., Wei X., Huang X., Huang L., Yang F., "Tribological properties of Al<sub>2</sub>O<sub>3</sub> nanoparticles as lubricating oil additives", Ceram Int; 40, pp. 7143–7149, 2014.
- [19]. Vasheghani M., Marzbanrad E., Zamani C., Aminy M., Raissi B., Badzadeh E. T., Barzegar-Bafrooei H., "Effect of Al<sub>2</sub>O<sub>3</sub> phases on the enhancement of thermal conductivity and viscosity of nano fluids in engine oil", Heat Mass Transfer, 47, pp. 1401–1405, 2011.
- [20]. Tang Z., Li S., "A review of recent developments of friction modifiers for liquid lubricants (2007-present)", Current Opinion in Solid State and Materials Science, 18, pp. 119–139, 2014.
- [21]. Rashed A., Nabhan A., "Friction and Vibration Analysis of Sliding Surfaces Lubricated by Engine Oils Dispersed by Aluminum Oxide Nanoparticles" Journal of the Egyptian Society of Tribology (EGTRIB Journal), 17(1), pp. 14-26, 2020.
- [22]. Nabhan A., Rashed A., "Anti-wear Effect and The Role of the Dispersion Temperature of the Nanofluids Containing Al<sub>2</sub>O<sub>3</sub> Nanoadditives" Journal of the Egyptian Society of Tribology (EGTRIB Journal), 17(3), pp. 1-13, 2020.
- [23]. Ingole S, Charanpahari A, Kakade A, Umare S S, Bhatt D V, Menghani J. Tribological behavior of nano TiO<sub>2</sub> as an additive in base oil. Wear 2013; 301: 776–85.
- [24]. Wu Y,Tsui W,Liu T. Experimental analysis of tribological properties of lubricating oils with nanoparticle additives. Wear; 262: 819– 25, 2007.
- [25]. Shenoy B, Binu K, Pai R, Rao D, Pai R S. Effect of nanoparticles additives on the performance of an externally adjustable fluid film bearing. Tribol Int; 45: 38–42, 2012.
- [26]. Kao M J, Lin C R. Evaluating the role of spherical titanium oxide nanoparticles in reducing friction between two pieces of cast iron. J Alloys Compd; 483: 456–9, 2009.
- [27]. Arumugam S, Sriram G. Preliminary study of nano and micro scale TiO<sub>2</sub> additives on tribological behavior of chemically modified rapeseed oil. Tribol Trans; 56: 797–805, 2013.
- [28]. Nabhan A., Ghazaly N. M., Mousa H. M., Rashed A.," Influence of TiO<sub>2</sub> and SiO<sub>2</sub> Nanoparticles Additives on the Engine Oil Tribological Properties: Experimental Study at Different Operating Conditions" International Journal of Advanced Science and Technology, 29(1), pp. 845-855, (2020).
- [29]. Peng D. X., Kang Y., Hwang R. M., Shyr S. S., Chang Y. P., "Tribological properties of diamond and SiO<sub>2</sub> nanoparticles added in paraffin," Tribol. Int., vol. 42, no. 6, pp. 911–917, 2009.
- [30]. Peng D., Chen C., Kang Y., Chang Y., Chang S., "Size effects of SiO<sub>2</sub> nanoparticles as oil additives on tribology of lubricant," Industrial Lub. and Tribology, 62(2), pp. 111–120, 2010.
- [31]. Xie H., Jiang B., He J., Xia X., Pan F., "Lubrication performance of MoS<sub>2</sub> and SiO<sub>2</sub> nanoparticles as lubricant additives in magnesium alloy-steel contacts," Tribology Int., 93, pp. 63–70, 2016.
  [32]. Chaudhary S., Singh R. C., Chaudhary R., "Experimental Investigation of Influence of SiO<sub>2</sub> Nanoparticles on the Tribological and
- [32]. Chaudhary S., Singh R. C., Chaudhary R., "Experimental Investigation of Influence of SiO<sub>2</sub> Nanoparticles on the Tribological and Rheological properties of SAE 40 Lubricating Oil," International Journal of Engineering and Technology, 9(6), pp. 4307–4314, 2018.
- [33]. Dubey M. K., Bijwe J., Ramakumar S. S. V., "PTFE based nano-lubricants", Wear, 306, pp.80–88, 2013. DOI: 10.1016/j.wear.2013.06.020.
- [34]. Dubey M. K., Bijwe J., Ramakumar S. S. V., "Nano-PTFE: new entrant as a very promising EP additive", Tribology International, 87, pp. 121–131, 2015. DOI: 10.1016/j.triboint.2015.01.026.
- [35]. Dubey M. K., Bijwe J., Ramakumar S. S. V., "Effect of dispersant on nano-PTFE based lubricants on tribo-performance in fretting wear mode", RSC Adv., 6, pp. 22604–22614, 2016. DOI: 10.1039/C5RA16795G.
- [36]. Saini V., Bijwe J., Seth S., Ramakumar S. S. V., "Role of base oils in developing extreme pressure lubricants by exploring nano-PTFE particles", Tribology International, 143, 106071, 2019. DOI: 10.1016/j.triboint.2019.106071.

www.ajer.org

2021

- Asrula M., Zulkiflia N. W. M., Masjukia H. H., Kalama M. A., "Tribological properties and lubricant mechanism of Nanoparticle in [37]. Engine Oil", Procedia Engineering, 68, pp. 320-325, 2013.
- [38]. Bhaumik S., Pathak S. D., "Analysis of anti-wear properties of CuO nanoparticles as friction modifiers in mineral oil (460cSt Viscosity) using pin-on-disk tribometer", Tribol. Indust., 37 (2), pp. 196–203, 2015.
- Saxena N. D., Chauhan N., "An overview on characterization of CuO based nano lubricant", Materials Today: Proceedings, 2019. [39]. DOI: 10.1016/j.matpr.2019.12.206.
- [40]. Sastry N. N. V., Avijit B., Sundararajan T., Sarit K. D., "Predicting the effective thermal conductivity of carbon nanotube based nanofluids", Nanotechnology 19 (5), pp. 055704–055708, (2008). Sharma S. K., Gupta S. M., "Preparation and evaluation of stable nanofluids for heat transfer application: a review", Exp. Thermal
- [41]. Fluid Sci., 79. pp. 202-212, 2016.
- Devendiran D. K., Amirtham V. A., "A review on preparation, characterization, properties and applications of nanofluids", Renew. [42]. Sust. Energ. Rev., 60, pp. 21-40, 2016.
- Sharma A. K., Katiyar J. K., Bhaumik S., Roy S., Influence of alumina/MWCNT hybrid nanoparticle additives on tribological [43]. properties of lubricants in turning operations", Friction, pp. 1-16, 2018.
- [44]. Akhgar A., Toghraie D., "An experimental study on the stability and thermal conductivity of water-ethylene glycol/TiO2-MWCNTs hybrid nanofluid: developing a new correlation", Powder Technol. 338, pp. 806-818, 2018.
- Asadi M., Asadi A., "Dynamic viscosity of MWCNT/ZnO-engine oil hybrid nanofluid: an experimental investigation and new [45]. correlation in different temperatures and solid concentrations", Int. Commun. Heat Mass Transf., 76, pp. 41-45, 2016.
- Ghaffarkhah A., Bazzi A., Dijvejin Z. A., Talebkeikhah M., Moraveji M. K., Agin F., "Experimental and numerical analysis of [46]. rheological characterization of hybrid nano-lubricants containing COOH-Functionalized MWCNTs and oxide nanoparticles", Int. Commun. Heat Mass Transf., 101, pp. 103-115, 2019.
- Rashed A., Nabhan A., "Effects of TiO2 and SiO2 Nano Additive to Engine Lubricant Oils on Tribological Properties at Different [47]. Temperatures" 20th Int. Conf. on Aerospace, Mech., Automotive and Mat. Eng., Rome, Italy, 2018.
- Jiao D., Zheng S., Wang Y., Guan R., Cao B., "The tribology properties of alumina/silica composite nanoparticles as lubricant [48]. Additives", Applied Surface Science, 257, 5720 - 5725, 2011.
- Bahramian A., Raeissi K., Hakimizad A., "An investigation of the characteristics of Al2O3/TiO2 PEO nano composite coating", [49]. Appl. Surf. Sci., 351, 13-26, 2015.
- Ali M. K. A., Xianjun H., Mai L., Bicheng C., Turkson R. F., Qingping C., "Reducing frictional power losses and improving the [50]. scuffing resistance in automotive engines using hybrid nanomaterials as nano-lubricant additives", Wear, 364-365, 270-828, 2016.
- Ali M. K. A., Xianjun H., Essa F. A., Abdelkareem M. A. A., Elagouz A., Sharshir S. W., "Friction and Wear Reduction [51]. Mechanisms of the Reciprocating Contact Interfaces using Nanolubricant under Different Loads and Speeds", Journal of Tribology, 140(5), 051606, 2018
- Nam S. R., Jung C. W., Choi C.-H., and Kang Y. T., "Cooling performance enhancement of LED (light emitting diode) packages [52]. with carbon nano grease," Energy, 60, 195-203, 2013.
- Juha Miettinen, Peter Andersson. Acoustic emission of rolling bearings lubricated with contaminated grease. Tribology [53]. International, 33, 777-787, 2000.
- [54]. Eman Ahmed, Nabhan A., Nouby M., Abd El-Jaber, G.T.," Influence of Adding Contaminants particles to Lithium Grease on the Frictional Coefficient" Journal of the Egyptian Society of Tribology (EGTRIB Journal), 14(1), pp. 15-29, 2017.
- Samy, A. M. Ali, W. Y., "Developing the tribological properties of lithium greases to withstand abrasion of machine elements in [55]. dusty environment", International Journal of Scientific & Engineering Research, 4 (10), pp. 1176-1181, 2013.
- [56]. Ricardo Serrato, Marcia Maru and Linilson Padovese. Effect of lubricant oil viscosity and contamination on the Mechanical signature of roller bearing. 12<sup>th</sup> International Conference on Sound and Vibration, 87, 514-567, 2005.
- [57]. R. Serrato, M.M. Maru, L.R. Padovese. Effect of lubricant viscosity grade on mechanical vibration of roller bearings. Tribology International, 40, 1270-1275, 2007.
- [58]. M.M. Maru, R.S. Castillo, L.R. Padovese. Study of solid contamination in ball Bearings through vibration and wear analyses. Tribology International, Vol. 40, 433-44. 2006.
- Marcia Marie Maru, Ricardo Serrato Castillo, Linilson Rodrigues Padovese. Effect of the Presence of Solid Contamination and the [59]. Resulting Wear on the Mechanical Signature of Ball Bearings. 18th Int. Congress of Mechanical Engineering, Ouro Preto, MG, 2005.
- [60]. Onkar L. Mahajan, Abhay A. Utpat. Study of Effect of Solid Contaminants in the Lubricant on Ball Bearings Vibration. International Journal of Instrumentation, Control and Automation (IJICA), 1, 2012.
- Yogesharao Y. More, A.P.Deshmukh. Study of Effect of Solid Contaminants in Grease on Performance of Ball Bearing by [61]. Vibrationan Analysis. International Journal of Innovations in Engineering Research and Technology [IJIERT], 2 (5), 2015.
- Sachin P. Godase, S. S. Nehe, B. Anatharama. Analysis of Effect of Solid Contaminants in Lubrication on vibration response of Ball [62]. bearing. International Engineering Research Journal (IERJ), 1(7), 545-549, 2015.
- [63]. Johnson R. L., "A review of the Early Use of Molybdenum Disulphide as a Lubricant", NLGI Spokesman, 32 p. 238, 1968.
- Benea L, Mardare-Danaila E and Celis JP. Increasing the tribological performances of Ti-6Al-4V alloy by forming a thin [64]. nanoporous TiO<sub>2</sub> layer and hydroxyapatite electrodeposition under lubricated conditions. Tribol Int; 78: 168–175, 2014.
- Ye W, Cheng T, Ye Q, et al. Preparation and tribological properties of tetrafluorobenzoic acid-modified TiO<sub>2</sub> nanoparticles as [65]. lubricant additives. Mater Sci Eng A; 359: 82-85, 2003.
- Ing TC, Rafiq AKM, Azli Y, et al. Tribological behavior of refined bleached and deodorized palm olein in different loads using a [66]. four-ball tribotester. Sci Iran; 19: 1487-1492, 2012.
- [67]. Li BL, Li ZG and Gao ZL. Experimental study on tribological performance of lithium grease containing various nano-particles as reconditioned additives. Lubr Eng; 2: 150, 2007.
- [68]. Li BL, Li ZG, Luo GZ, et al. Experimental study of tribological properties of various nanoparticles as additive in lubrication of lithium grease. J Dalian Railw Inst; 3: 9, 2006.
- Chang H, Lan CW, Chen CH, et al. Anti-wear and friction properties of nanoparticles as additives in the lithium grease. Int J Prec [69]. Eng Manuf; 15: 2059-2063, 2014.
- [70]. He Qiang, Tao Wang1, Hongwen Qu, Yong Zhang, Anling Li and Linghao Kong. Tribological and rheological properties of nanorods-Al2O3 as additives in grease, Proc IMechE Part J: J Engineering Tribology, 233 (4), 605-614, 2018.
- Wang L., Wang B., Wang X., and Liu W., "Tribological investigation of CaF2 nanocrystals as grease additives," Tribol. Int., 40, pp. [71]. 1179-1185, 2007.
- [72]. Ji X., Chen Y., and Zhao G., "Tribological Properties of CaCO<sub>3</sub> Nanoparticles as an Additive in Lithium Grease," Tribol. Lett., 41, pp. 113 - 119, 2011.

2021

- [73]. Mohamed, T. A. Osman, A. Khattab, and M. Zaki, "Tribological Behavior of Carbon Nanotubes as an Additive on Lithium Grease," Journal of Tribology, 137, pp. 1 - 5, 2015.
- [74]. Nabhan A., Vibration analysis of adding contaminants particles and carbon nanotubes to lithium grease of ball bearing, The 22<sup>nd</sup> International Conference on Vibroengineering – Moscow, Vibroengineering Procedia, 8, 28 - 32, 2016.
- [75]. Stolzenburg, P.; Hämisch, B.; Richter, S.; Huber, K.; Garnweitner, G. Secondary Particle Formation during the Nonaqueous Synthesis of Metal Oxide Nanocrystals. Langmuir, 34, 12834–12844.2018.
- [76]. Liu, D.; Zhang, M.; Zhao, G.; Wang, X. Tribological Behavior of Amorphous and Crystalline Overbased Calcium Sulfonate as Additives in Lithium Complex Grease. Tribol. Lett., 45, 265–273, 2011.
- [77]. Mohamed, A.; Khattab, A.; Osman, T.A.; Zaki, M. Influence of Nano Grease Composite on Rheological Behaviour. Int. J. Eng. Res. Appl., 3, 1126–1131, 2013.
- [78]. Eman Ahmed, Nabhan A., Nouby M., Abd El-Jaber, G.T.," Influence of Dispersing Lithium Grease by Hybrid Nano Titanium and Silicon Oxides on Friction Coefficient" Journal of the Egyptian Society of Tribology (EGTRIB Journal), 15(3), 61-71, 2018.
- [79]. A. Margolin, R. Popovitz-Biro, A. Albu-Yaron, L. Rapoport, and R. Tenne, "Inorganic fullerene-like nanoparticles of TiS2," Chem. Phys. Lett., 411 1-3, 162-166, 2005.
- [80] L. Rapoport, V. Leshchinky, Y. Volovik, M. Lvovsky, O. Nepomnyashchy, Y. Feldman, R. Popovitz-Biro, and R. Tenne, "Modification of contact surfaces by fullerine-like solid lubricant nanoparticles," Surf. Coatings Technology, 163-164, 405-412, 2003.
- [81]. W. L. G. Zhao, Q. Zhao, W. Li, X. Wang, "Tribological properties of nano-calcium borate as lithium grease additive," Lubr. Sci., 26, 43-53, 2009.
- [82]. X. Fan, Y. Xia, L. Wang, and W. Li, "Multilayer Graphene as a Lubricating Additive in Bentone Grease," Tribol. Lett., 455-464, 2014.
- [83]. Z.-L. Cheng and X.-X. Qin, "Study on friction performance of graphene-based semi-solid grease," Chinese Chem. Lett., 25, pp. 1305-1307, 2014.
- [84]. J. Chen, "Tribological Properties of Polytetrafluoroethylene, Nano-Titanium Dioxide, and Nano-Silicon Dioxide as Additives in Mixed Oil-Based Titanium Complex Grease," Tribol. Lett., 38 (3), 217-224, 2010.
- [85]. L. Peña-Parás, J. Taha-Tijerina, a. García, D. Maldonado, a. Nájera, P. Cantú, and D. Ortiz, "Thermal transport and tribological properties of nanogreases for metal-mechanic applications," Wear, 332-333, 1322-1326, 2015.
- [86]. L. Wang, M. Zhang, X. Wang, and W. Liu, "The preparation of CeF 3 nanocluster capped with oleic acid by extraction method and application to lithium grease," Mater. Res. Bull., 43, 2220-2227, 2008.
  [87]. X. Ji, Y. Chen, and G. Zhao, "Tribological Properties of CaCO<sub>3</sub> Nanoparticles as an Additive in Lithium Grease," Tribol. Lett., 41
- [87]. X. Ji, Y. Chen, and G. Zhao, "Tribological Properties of CaCO<sub>3</sub> Nanoparticles as an Additive in Lithium Grease," Tribol. Lett., 41 (1), 13-119, 2011.

Nabhan A, et. al. "Tribological Behavior and Performance of Lubricants Filled with Nanoparticles: A Review."*American Journal of Engineering Research (AJER)*, vol. 10(1), 2021, pp. 230-236.

www.ajer.org

2021